

PRODUCT DATA SHEET

Avery Dennison® MPI™ 3000 Gloss High Opacity Series

issued: 08/2020

Introduction

Avery Dennison Multi Purpose Inkjet 3000 High Opacity series (HOP) films are gloss white, self-adhesive short-term calendered vinyls with high opacity properties, offering a choice between permanent and removable adhesives.

MPI 3000 Gloss HOP film features such as high opacity (above 99%), clear permanent and removable adhesive and good printability with attractive whiteness make it an optimal solution for a wide range of short-term, promotional applications, allowing customers to significantly reduce their inventory.

MPI 3004 HOP Easy Apply, part of MPI 3000 HOP series, is using Easy Apply technology allowing fast and easy bubble free application for effective promotions and short-term flat applications.

Description

Film	: MPI 3000/3001 HOP MPI 3004 HOP EA	95 micron gloss white high opacity 95 micron gloss white high opacity
Adhesive	: MPI 3000 HOP MPI 3001 HOP MPI 3004 HOP EA	Permanent, clear, acrylic based Removable, clear, acrylic based Removable, clear, acrylic based
Backing paper	: MPI 3000/3001 MPI 3004 HOP EA	Clay coated kraft paper, 125 g/m2 Clay coated kraft paper with air egress channels, 136 g/m2

Conversion

MPI 3000 Gloss HOP series films are multi-purpose vinyls, suitable for a variety of wide format inkjet printers using hard solvent, eco/mild solvent, UV-curing or latex inks.

To enhance colour and to protect images against UV radiation and abrasion, it is recommended to protect Avery Dennison MPI 3000 Gloss HOP series films using an overlamine or varnish.

For recommended combinations of DOL films and media, please refer to "Technical Bulletin 5.3. Recommended combinations of Avery Dennison® Overlaminates and Avery Dennison® Digital Print Media".

Uses

- Interior & exterior signs, including over posting applications
- Window decoration
- Promotional, point of sale, advertising applications on flat surfaces

Features

- Excellent printability and handling on selected printers
- Superior whiteness and high opacity properties film
- Easy cutting and application on a wide variety of substrates
- High opacity film with clear permanent or removable adhesive constructions allow to cover a wide range of applications and significantly reduce customer inventory
- MPI 3004 HOP Easy Apply enabling fast and easy application, cover-up performance for effective promotions

PRODUCT CHARACTERISTICS series

Avery Dennison® MPI™ 3000 HOP

Physical properties

Features	Test method ¹	Results
Caliper, face film	ISO 534	95 micron
Dimensional stability	FINAT FTM 14	0.3 mm max.
Opacity	ISO 2471	> 99 %*
* Not a blackout film, opacity on par with MPI 3002/3003		
MPI 3000 HOP		
Adhesion, initial	FINAT FTM-1, stainless steel	510 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	875 N/m
MPI 3001 HOP		
Adhesion, initial	FINAT FTM-1, stainless steel	180N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	280N/m
MPI 3004 HOP EA		
Adhesion, initial	FINAT FTM-1, stainless steel	310 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	465 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability, unprinted	Vertical exposure	3years

Temperature range

Features	Results
Minimum application temperature:	≥ 10° C
Temperature range:	- 40 to +85 °C

NOTE: Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24 hours before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of these Conditions, the English version shall be controlling.

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

1) Test methods

More information about our test methods can be found on our website.

2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.